

UPM Office Green (APAC)

Choose UPM Office cut-size papers when you need to be absolutely sure to produce optimal printing quality. Suitable for anything from superior-quality colour printouts to functional high speed copying.

Recommended end-uses

Correspondence | Documents | Fax papers | Memos | Office applications | Office paper | Reports | Routine communication

Product information

| Regions | Asia-Pacific | | |
|------------------|--|--|--|
| Business contact | UPM Specialty Papers | | |
| Category | Office papers Digital printing papers | | |
| Description | High-white, uncoated woodfree allround paper. | | |
| Grade | Woodfree uncoated (WFU) | | |
| Finish | Machine finished | | |
| Furnish | Fillers Chemical pulp | | |
| Printing method | B/W inkjet printing B/W laser printing (dry toner) Colour laser printing (dry toner) Copying Fax | | |
| Format/Size | A4 A3 Sheets | | |
| Wrapping | Strong moisture proof polyethylene laminated kraft paper | | |
| Note | Available in Asia-Pacific. ISO 9706 on request. | | |

Certificates

| Product Compliance | China Green Label Permanent Paper ISO 9706 |
|-----------------------|---|
| Fibre Certificates | FSC Chain-of-Custody PEFC Chain-of-Custody |
| Mill Certificates | China Green Label EMAS ISO 9001 ISO 45001 ISO 14001 |

Technical target values

| Basis Weight (ISO 536) (g/m²) | 70 | 75 | 80 |
|---|-----|-----|-----|
| Thickness (ISO 534) (µm) | 99 | 104 | 109 |
| CIE Whiteness (ISO 11475) (%) | 167 | 167 | 167 |
| Brightness D65 (ISO 2470-2) (%) | 111 | 111 | 111 |
| Opacity (ISO 2471) (%) | 93 | 94 | 95 |
| Roughness Bendtsen (ISO 8791-2) (ml/min) | 220 | 220 | 220 |
| Moisture (ISO 287) (%) | 4.5 | 4.5 | 4.5 |

Please note: Technical values are informative and subject to production variations.