

# **UPM** Prego<sup>™</sup>

 $\mathsf{UPM}\,\mathsf{Prego}^\mathsf{TM}\,\mathsf{is}\,\mathsf{a}\,\mathsf{barrier}\,\mathsf{base}\,\mathsf{paper}\,\mathsf{for}\,\mathsf{packaging}\,\mathsf{of}\,\mathsf{baked}\,\mathsf{goods}\,\mathsf{and}\,\mathsf{food}\,\mathsf{to}\,\mathsf{go}\,\mathsf{with}\,\mathsf{a}\,\mathsf{natural}\,\mathsf{look}\,\mathsf{and}\,\mathsf{feel}.\,\mathsf{It's}\,\mathsf{recyclable}\,\mathsf{and}\,\mathsf{compostable}.$ 

● Recyclable ● Compostable ● Flexo ● Coating base

#### **Recommended end-uses**

Bags | Coating | Wraps

#### **Product information**

Regions	Europe   North America   Asia-Pacific   Latin America   Middle East & India   Africa   China
Business contact	UPM Specialty Papers
Category	Packaging papers
Grade	Barrier base
Printing method	Flexo   Offset
Reel diameter (cm)	80,0 - 120,0
Reel width (cm)	50,0 - 240,0
Core (mm)	76,0 / 153,0
Note	Note FSC™ and PEFC on request but subject to availability (FSC C014719, PEFC/02-31-80).

## Certificates

Product Compliance	BfR Food Certificate   FDA Food Certificate   EN 71-3: Safety of Toys
Fibre Certificates	FSC Chain-of-Custody   PEFC Chain-of-Custody
Mill Certificates	ISO 9001   ISO 14001   ISO 22000   ISO 45001   EMAS
End of life	Recyclable   Home Compostable   Industrially Compostable

## Technical target values with metric units

Basis weight (ISO 536) (g/m²)	45.0	55.0	
Thickness (ISO 534) (µm)	53.0	62.0	
Brightness C/2° (ISO 2470) (%)	82.0	80.0	
Opacity ISO (2471) (%)	72.0	75.0	
WVTR 23°C / RH 50% (g/m²/d)	100	100	

## Technical target values with imperial units

Basis weight (ISO 536) (lb/3300ft²)	30.4	37.1
Thickness (ISO 534) (mils)	2.1	2.4
Brightness C/2° (ISO 2470) (%)	82.0	80.0
Opacity ISO (2471) (%)	72.0	75.0
WVTR 23°C / RH 50% (g/m²/d)	100	100

Please note: Technical values are informative and subject to production variations.