



The Biofore Company

UPM



# UPM Ultra

UPM Ultra is designed to meet bottom line results. Choose UPM Ultra when seeking an ideal sheet to provide consistent press performance with crisp image reproduction. Recommended end-uses include publications, catalogs, inserts and books.

## FEATURES

<b>BRIGHTNESS</b>	78–84
<b>FINISHES</b>	Gloss, Silk, Matte
<b>WEIGHT</b>	Available in both North American and European text weights ranging from 36 lbs.–54.1 lbs.
<b>GRADE</b>	#4 coated groundwood, heatset web offset and gravure

## BENEFITS

- Excellent runability
- Versatility for broad print applications
- High quality image reproduction
- Wide range of basis weights offering slight or considerable alternatives
- FSC® and PEFC™ available upon request but subject to availability

## APPLICATIONS

Catalogs, magazines, books, inserts, bookazines, commercial print, flyers and custom publishing.

EMAS, EU Ecolabel, FSC® Chain-of-Custody, ISO 14001, ISO 50001, ISO 9001, OHSAS 18001, PEFC™ Chain-of-Custody

For more information or to request samples, visit [www.upm.com/na](http://www.upm.com/na) or call **1-877-876-8700**.

	BASIS WEIGHTS (lbs.)	GSM (g/m <sup>2</sup> )	BRIGHTNESS (GE)	OPACITY (TAPPI)	GLOSS (HUNTER)	MILL(S)
<b>HEATSET WEB OFFSET</b>						
UPM Ultra H	36	53.3	80	87; 86	56; 55	Blandin; Caledonian, Rauma
	36.5	54	80	86	58	Caledonian, Rauma
	38	56.2	80	87; 88	61; 58	Blandin; Caledonian, Rauma
	38.5	57	80	88	58	Caledonian, Rauma
	40	59.2	80; 81	88	61; 60	Blandin; Caledonian, Rauma
	40.5	60	81	88	60	Caledonian, Rauma
	43.9	65	83	90	64	Rauma
	45	66.6	81, 83	90	64	Blandin, Rauma
	47.3	70	83	91	64	Rauma
	50	74	84	92	66	Rauma
	50.7	75	84	92	66	Rauma
	54.1	80	84	93	66	Rauma
UPM Ultra Plus H	38	56.2	83	87	61	Blandin
	40	59.2	83	88	61	Blandin
	45	66.6	84	90	64	Blandin
UPM Ultra Silk H	40	59.2	80	89	38	Blandin
	40.5	60	80	89	40	Caledonian
	43	63.6	81	90	38	Blandin
	43.9	65	82	90	40	Caledonian
	45	66.6	81	91	38	Blandin
UPM Ultra Matte H	36.5*	54	81	87	30	Rauma
	38.5	57	81	88	30	Rauma
	40.5	60	81	90	30	Rauma
	43.9	65	81	91	30	Rauma
	47.3	70	82	92	30	Rauma
<b>ROTOGRAVURE</b>						
UPM Ultra G	34.5*	51	78	90	55	Kaipola, Rauma
	36	53.3	78	90	60	Kaipola, Rauma
	36.5	54	78	90	60	Kaipola, Rauma
	38	56.2	80	90	63	Kaipola, Rauma
	38.5	57	80	90	63	Kaipola, Rauma
	40	59.2	81	91	65	Kaipola, Rauma
	40.5	60	81	91	65	Kaipola, Rauma
	43.9	65	84	92	66	Rauma, Kaukas*
	45*	66.6	84	92	67	Rauma, Kaukas*
	47.3	70	84	93	68	Rauma, Kaukas*
UPM Ultra Silk G	38.5*	57	80	91	45	Kaipola
	40.5	60	81	91	45	Kaukas

\*Available upon request.

Values are subject to change.



[www.upm.com/na](http://www.upm.com/na)



**North American Headquarters**  
 55 Shuman Boulevard  
 Naperville, IL 60563  
 Tel. (630) 922-2500  
 Fax (630) 922-2504  
[paperinfo@upm.com](mailto:paperinfo@upm.com)



Scan to view or save a digital version.