

## UPM FINESSE GLOSS G

Consistently high quality, realistic printing results and vibrant images. Use UPM Finesse when you want to impress your readers. Main end-uses for UPM Finesse are magazines, prestigious catalogs and advertising materials.

### UPM FINESSE GLOSS G:

|                                |   |
|--------------------------------|---|
| <b>Category</b>                | Rotogravure papers  |
| <b>Grade</b>                   | Woodfree coated (WFC)   |
| <b>End use</b>                 | Advertising material   Brochures   Catalogues   Direct mailing   High-quality magazines   Magazine covers   Magazines   |
| <b>Finish</b>                  | Gloss   |
| <b>Printing method</b>         | Rotogravure   |
| <b>Format/Size</b>             | Reels   |
| <b>Reel Diameter (cm)</b>      | 125,0   |
| <b>Reel Width (cm)</b>         | 24,0 - 250,0  |
| <b>Core (mm)</b>               | 76,0 / 152,0  |
| <b>Wrapping</b>                | Strong moisture proof polyethylene laminated kraft paper  |
| <b>Certificates and labels</b> | 94/62 EC Heavy Metal Certificate   BfR Food Certificate   EMAS   EN 71/3:1988 D Safety of Toys   EU Ecolabel   FSC Chain-of-Custody   ISO 14001   ISO 50001   ISO 9001   OHSAS 18001   PEFC Chain-of-Custody   Permanent Paper ISO 9706 |
| <b>Note</b>                    | FSC® and PEFC™ on request but subject to availability.<br>Reel widths 250.1-272.0 available on request.   |

## TECHNICAL TARGET VALUES:

|   |       |       |
|---|-------|-------|
| <b>Basis Weight (ISO 536) (g/m<sup>2</sup>)</b> | 115.0 | 130.0 |
| <b>Bulk (ISO 534) (cm<sup>3</sup>/g)</b>        | 0.74  | 0.74  |
| <b>Brightness D65 (ISO 2470-2) (%)</b>          | 98.0  | 98.0  |
| <b>CIE Whiteness (%)</b>                        | 122.0 | 122.0 |
| <b>L-value D65 (D65/10°) (ISO 5631-2)</b>       | 95.0  | 95.0  |
| <b>a-value D65 (D65/10°) (ISO 5631-2)</b>       | 1.8   | 1.8   |
| <b>b-value D65 (D65/10°) (ISO 5631-2)</b>       | -7.6  | -7.6  |
| <b>Opacity ISO (2471) (%)</b>                   | 93.0  | 94.5  |
| <b>Gloss Hunter (ISO 8254-1) (%)</b>            | 80.0  | 80.0  |
| <b>Smoothness PPS 10 (ISO 8791-4) (µm)</b>      | 0.7   | 0.7   |

**Please note: Technical values are informative and subject to production variations.**