

## UPM JETLABEL

Are high whiteness, good printability and runnability your priorities? Then choose from these machine or supercalendered, woodfree uncoated papers for your converting purposes.

### UPM JETLABEL:

<b>Category</b>	Face papers
<b>Grade</b>	Woodfree uncoated (WFU)
<b>End use</b>	VIP labelling
<b>Finish</b>	Machine finished
<b>Furnish</b>	Hardwood and softwood sulphate pulp
<b>Printing method</b>	Colour inkjet printing   Colour laser printing (dry toner)   Flexo   Letterpress   Offset
<b>Format/Size</b>	Reels
<b>Reel Diameter (cm)</b>	100,0 - 140,0
<b>Reel Width (cm)</b>	50,0 - 283,0
<b>Core (mm)</b>	71,0 / 76,0 / 152,0
<b>Wrapping</b>	Strong kraft paper   Strong moisture proof polyethylene laminated kraft paper
<b>Certificates and labels</b>	94/62 EC Heavy Metal Certificate   BfR Food Certificate   EMAS   EU Ecolabel   FSC Chain-of-Custody   ISO 14001   ISO 9001   OHSAS 18001   PEFC Chain-of-Custody   Permanent Paper ISO 9706
<b>Note</b>	PEFC and FSC on request but subject to availability.

## TECHNICAL TARGET VALUES:

<b>Basis Weight (ISO 536) (g/m<sup>2</sup>)</b>	65.0	70.0
<b>CIE Whiteness (ISO 11475:2017) (%)</b>	165.0	165.0
<b>Opacity ISO (2471) (%)</b>	90.0	92.0
<b>Roughness Bendtsen (ISO 8791-2) (ml/min)</b>	150.0	150.0
<b>Thickness (ISO 534) (μm)</b>	84.0	89.0
<b>Tensile Strength MD (kN/m)</b>	5.3	5.5
<b>Tensile Strength CD (kN/m)</b>	2.2	2.3
<b>Tear Strength CD (mN)</b>	500.0	530.0

**Please note: Technical values are informative and subject to production variations.**