

# UPM Office Green (APAC)

Choose UPM Office cut-size papers when you need to be absolutely sure to produce optimal printing quality. Suitable for anything from superior-quality colour printouts to functional high speed copying.

## Recommended end-uses

Correspondence | Documents | Fax papers | Memos | Office applications | Office paper | Reports | Routine communication

## Product information

<b>Regions</b>	Asia-Pacific
<b>Business contact</b>	<b>UPM Specialty Papers</b>
<b>Category</b>	Office papers   Digital printing papers
<b>Description</b>	High-white, uncoated woodfree allround paper.
<b>Grade</b>	Woodfree uncoated (WFU)
<b>Finish</b>	Machine finished
<b>Furnish</b>	Fillers   Chemical pulp
<b>Printing method</b>	B/W inkjet printing   B/W laser printing (dry toner)   Colour laser printing (dry toner)   Copying   Fax
<b>Format/Size</b>	A4   A3   Sheets
<b>Wrapping</b>	Strong moisture proof polyethylene laminated kraft paper
<b>Note</b>	Available in Asia-Pacific. ISO 9706 on request.

## Certificates

<b>Product Compliance</b>	China Green Label   Permanent Paper ISO 9706
<b>Fibre Certificates</b>	FSC Chain-of-Custody   PEFC Chain-of-Custody
<b>Mill Certificates</b>	China Green Label   EMAS   ISO 9001   ISO 45001   ISO 14001

## Technical target values

<b>Basis Weight (ISO 536) (g/m<sup>2</sup>)</b>	<b>70</b>	<b>75</b>	<b>80</b>
<b>Thickness (ISO 534) (µm)</b>	99	104	109
<b>CIE Whiteness (ISO 11475) (%)</b>	167	167	167
<b>Brightness D65 (ISO 2470-2) (%)</b>	111	111	111
<b>Opacity (ISO 2471) (%)</b>	93	94	95
<b>Roughness Bendtsen (ISO 8791-2) (ml/min)</b>	220	220	220
<b>Moisture (ISO 287) (%)</b>	4.5	4.5	4.5

Please note: Technical values are informative and subject to production variations.