

## UPM PREINSERT, BOBINES

Soyez efficaces, réalisez vos documents commerciaux pré imprimés avec le papier non couché sans bois UPM Preprint. Il convient à la réalisation de formulaires, de papiers administratifs, d'en-têtes et de publipostages.

### UPM PREINSERT, BOBINES:

<b>Catégories papier</b>	Papiers postaux
<b>Qualité</b>	Non couché sans bois (WFU)
<b>Utilisation finale</b>	Cartes de visite   Formulaires commerciaux
<b>Finition</b>	Lissé/fini machine
<b>Composition</b>	Pâte chimique
<b>Procédé d'impression</b>	Impression jet d'encre n/b   Préimpression offset
<b>Format</b>	Bobine
<b>Diamètre bobine (cm)</b>	100,0 - 130,0
<b>Laize bobine (cm)</b>	24,0 - 250,0
<b>Mandrin (mm)</b>	70,0 / 76,0 / 152,0
<b>Emballage</b>	Papier kraft résistant   Papier kraft laminé de polyéthylène résistant à l'humidité
<b>Certificats</b>	94/62 EC Heavy Metal Certificate   BfR Food Certificate   EMAS   EN 71/3:1988 D Safety of Toys   Le Label écologique européen   FSC Chain-of-Custody   ISO 14001   ISO 50001   ISO 9001   OHSAS 18001   PEFC Chain-of-Custody   Permanent Paper ISO 9706
<b>Note</b>	FSC® and PEFC™ on request but subject to availability.

## TECHNICAL TARGET VALUES:

<b>Grammage (ISO 536) (g/m<sup>2</sup>)</b>	120.0	140.0	170.0
<b>Main (ISO 534) (cm<sup>3</sup>/g)</b>	1.22	1.17	1.13
<b>Blancheur CIE (%)</b>	147.0	147.0	147.0
<b>Opacité ISO (2471) (%)</b>	96.8	97.8	98.7
<b>Rugosité Bendtsen (ISO 8791-2) (ml/min)</b>	280.0	280.0	320.0
<b>Epaisseur (ISO 534) (µm)</b>	143.0	159.0	188.0

**Please note: Technical values are informative and subject to production variations.**